



# ChemMasters®

# Conset Grout™

Non-shrink, Non-metallic  
Cementitious Construction Grout

**SPECIALTY CONSTRUCTION PRODUCTS**

## P R O D U C T D A T A

### DESCRIPTION

**ChemMasters' Conset Grout**, is a non-shrink, non-metallic, construction grout used at dry pack, plastic, flowable, or fluid consistency. Meets or exceeds ASTM Standards C1107 and CRD C-621.

### ADVANTAGES

- Flowable and self consolidating
- May be placed at plastic consistency for increased strength requirements – up to 7,150 psi after 28 day cure
- Non-shrink for maximum load bearing
- Can be extended 50% for placements over 2 inches (5 cm) deep
- Natural aggregate matches the color of concrete
- Contains no oxidizing components, will not rust
- Pumpable for rapid placement on large projects

### USES

- |                  |                  |
|------------------|------------------|
| Building Columns | Hand Rails       |
| Bridge Beams     | Boiler Plates    |
| Sewers           | Precast Beams    |
| Precast Columns  | Dowels           |
| Fence Posts      | Highway Barriers |
| Anchor Bolts     | Base Plates      |
| Bed Plates       | Underpinnings    |
| Wall Panels      | Pipes/Sleeves    |

## TECHNICAL DATA

### Packaging

Container	lbs / kg	Pallet	Item#
Moisture proof bags	50 / 22.7	60	F2310.50
Bulk bags 1 cubic yard	3000 / 1364	na	F2310.30

### Yield per 50 lb (22.7 kg)

	ft <sup>3</sup>	m <sup>3</sup>
Plastic	0.42	0.012
Flowable	0.43	0.012
Fluid	0.45	0.013

### Flow ASTM C 230 Flow Table, water per 50 lb bag

	Pints	Liters	5 drops
Plastic	8	3.8	107%
Flowable	9	4.3	145%
fluid	9 to 10	4.3 to 4.7	30 seconds **

\* For Ohio D.O.T. keyway grouting use a maximum of 8.5 pints (4L) water per 50 lb (23kg bag) \*\* Flow Cone

### Set Times ASTM 191/Vicat Method—Hours to Set

	Initial	Final
Plastic	2.2	3.5
Flowable	2.2	3.5
Fluid	3.2	4.0

### Compressive Strength ASTM C 109 / C 109M 2" Cubes - psi @ x days to cure

	1	7	28
Plastic	2,775	6,160	7,150
Flowable	2,590	5,260	6,870
Fluid	2,100	4,920	6,030

### Expansion ASTM 1090 / CRD C 621 Moist Cured

	24 hrs	3days	14 days	28days
Fluid	0.03%	0.03%	0.02%	0.02%

### ASTM C827 Early Height Change

Average of two 3" x 6" cylinders	+ 1.2%
----------------------------------	--------

### VOLUME GROUTING

For applications over 2 inches (5 cm) deep, **Conset Grout** may be extended with up to 25 lbs (11 kg) of clean, SSD 3/8" (0.95 cm) pea gravel per bag. With 9 pints (4.3L) of water yield will increase to approximately 0.6ft<sup>3</sup> (0.017m<sup>3</sup>) When including pea gravel in the mix, flow will decrease significantly.



## ChemMasters®

An American Owned & Operated Company  
300 EDWARDS STREET • MADISON, OHIO 44057-3112 (440) 428-2105 • FAX (440) 428-7091 • ORDERLINE: (800) 486-7866 [www.chemmasters.net](http://www.chemmasters.net)

Nov 2013

## DIRECTIONS

Grouting is best accomplished at temperatures from 40° to 90°F (4° to 32°C). For extremely low or high temperatures, follow the ACI 305 Hot Weather Concreting or ACI 306 Cold Weather Concreting or consult ChemMasters' Technical Service Department for additional recommendations.

15 minute working time is based on 70°F (21°C) "as mixed" temperature. Mix water may be adjusted to maintain a consistent 70°F (21°C) "as mixed" temperature. At 90°F (32°C), mix water may be adjusted to 33°F (1°C). At 40°F (4°C), mix water may be adjusted to 90°F (32°C). Proportional mix water temperature adjustments may be made within this range to maintain a 70°F (21°C) "as mixed" temperature.

**PREPARATION:** The concrete substrate where the grout will be placed must be clean and free of any curing or sealing compounds, dust, dirt, oil or grease. The base should be textured where possible using a small chipping hammer. Presoak the substrate with water for 24 hours to prevent premature drying of the grout. Cover with wet burlap or polyethylene sheeting to retain moisture.

**FORMING:** Forms will be required for most grouting applications. Top edges of forms must be higher than bottom of base plate to be grouted. Seal bottom edges of forms to prevent grout from leaking. Construct forms with a larger gap, at least 2" (5 cm), between form and base being grouted. Use a slant board or construct a head box to direct flow of grout from front to back. Allow at least a 1" (2.5 cm) gap at backside of form to facilitate flow and allow air to escape in front of grout flow. All forms in contact with the grout must be coated with ChemMasters' **Release or Safe-Slip**.

**MIXING:** A paddle type mortar mixer, grout pump, or heavy duty 1/2" drill with mixing prop are required. Place approximately 80% of required water into clean pre-wet mixer or container. Use only as much water as needed to properly place the grout. Adding excess water decreases strength and expansion. **For Ohio Department of Transportation keyway grouting applications, use a maximum of 8.5 pints (4L) of water per bag of Conset Grout.**

When using aggregate add it to the water. Do not add sand or cement to **Conset Grout**. With mixer blades operating, open bag, gradually empty into mixer, mix for about 1 minute, add remaining water, and mix for 2 to 3 minutes. Following this sequence should eliminate lumping and keep mixer clean and free of excess buildup.

**PLACEMENT:** Always place grout from one side at a steady, continuous flow to push air out in front of grout flow, ensuring maximum surface bearing of the plate or base. Do not vibrate grout.

**CURING: Proper curing is required!** As soon as grout placement is complete, wet cure or use a ChemMasters' ASTM C 309 *Liquid Membrane Forming Curing Compound*. Contact ChemMasters Technical Service Department for recommendations.

If wet curing wet burlap may be used following the guidelines in ACI 351, *Grouting for Support of Equipment and Machinery*.

**CLEANUP:** Clean tools and equipment with warm water before material dries and hardens.

## LIMITATIONS

- Do not apply to frost covered or frozen surfaces or at substrate or ambient temperatures below 40°F (4°C). Follow ACI 305 *Hot Weather Concreting* and 306 *Cold Weather Concreting* guidelines for placement when temperature is below 40°F (4°F) or above 90°F (32°C).
- ChemMasters recommends the use of ChemGrout mixers and pumps for placements under large base-plates or with a difficult configuration
- Contact ChemMasters' Technical Service Staff for special recommendations on precision grouting, dry pack situations or unusual circumstances
- For close tolerance placement or heavy duty applications subjected to extreme thermal shock, chemical resist, extreme high strength or dynamic loading, consider the use of ChemMasters' **Gorilla Grout, Kemset, Met-Ox, Polytops CR, Polytops HF or Polytops CR Grout**

**Storage:** Store in a cool dry location off the ground. Unopened bags can be stored for up to 2 years when kept dry.

## CAUTIONS

May cause eye and respiratory tract irritation. Over exposure may cause skin irritation. Do not take internally. See current MSDS for additional precautions.

**Keep out of reach of children.**

Proper application is the responsibility of the user. ChemMasters can only make technical recommendations and cannot provide quality control on the jobsite.

### This Product is Formulated and Labeled for Industrial and Commercial Use Only

FOR BEST RESULTS AND SAFEST USAGE, USER IS SPECIFICALLY DIRECTED TO CONSULT THE CURRENT PRODUCT & SAFETY DATA SHEETS AND PACKAGE LABEL FOR THIS PRODUCT. We warrant our products to meet our published specifications and to be free from defects in materials and workmanship to the acceptable quality levels defined in these specifications. If acceptable quality levels are not specified, the acceptable quality levels will be those normally supplied by us for the product. We make no guarantee of the results to be obtained from the use of our products. The determination as to the adaptability of any of our products to the specific needs of the Buyer is solely Buyer's prerogative and responsibility. We are glad to offer suggestions on the use of our products. Nevertheless, there are no warranties given except such expresses warranties offered in connection with the sale of a particular product. Our liability shall be limited to replacement of, or refund of an amount not to exceed the purchase price attributed to, the goods as to which such claim is made. Our selection of one of these alternatives shall be Buyer's exclusive remedy. IN NO CASE SHALL WE BE LIABLE FOR CONSEQUENTIAL OR SPECIAL DAMAGES, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. THE FOREGOING WARRANTIES ARE IN LIEU OF ALL OTHER WARRANTIES, GUARANTEES, CO-CONDITIONS AND REPRESENTATIONS, EITHER EXPRESSED OR IMPLIED, WHETHER ARISING UNDER ANY STATUTE, COMMON LAW, USAGE OR TRADE, COURSE OF DEALING OR OTHERWISE, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.