



SPECIALTY CONSTRUCTION PRODUCTS

Polytops MMA Grout

Methyl Methacrylate Grout

P R O D U C T D A T A

DESCRIPTION

Polytops MMA Grout is a three component, methyl methacrylate based grout. **Polytops MMA Grout** sets very rapidly even in freezing temperatures to minimize downtime. It develops very high strength rapidly. When mixed, **Polytops MMA Grout** forms a flowable, non-shrink, durable polymer grout that has very high bond, compressive and flexural strength, resists freeze thaw damage, and has excellent chemical resistance.

USES

- Grouting of bearing plates on bridges and trestles
- Rehabilitation of bridge decks, airport runways, and expansion joints
- Column grouting

ADVANTAGES

- For full bearing of base plates
- Self leveling for ease of placement
- Wide range of temperature applications from 0 to 100 °F (-18 to 38°C)
- Cures rapidly for emergency grouting applications
- Develops high compressive, tensile, and flexural strengths; withstands high levels of abrasion and impact loading
- Excellent bond to existing concrete
- Flexibility to withstand vigorous thermal cycling
- Freeze thaw resistant
- Excellent resistance to acids and alkalizes
- Exceptional ultraviolet light stability

Packaging/Part Number

6 gallon (78 lb) package containing: 1 gal (3.8L) MMA Resin Part A 14 ounces (0.414 ml) Catalyst Part B 70 lb (32kg) Aggregate Part C	F5370.78
--	----------

TECHNICAL DATA

USDA approved for incidental contact in federally inspected meat, fish and poultry plants.

Test Data

AASHTO T237 Pot Life @70°F (21°C)	20 to 30 minutes
Elongation	3 to 5%
Yield Neat Extended with 25 lbs #8 pea gravel	0.58 ft ³ 0.75ft ³
ASTM C 109 Compressive Strength Neat 1 hour @ 19°F 1 hours @ 70°F 3 hours @ 70°F 24 hours @ 70°F Extended 1 hour @19°F 1 hour @100°F 24 hours @ 70°F	3,850 psi 5,500 psi 7,100 psi 7,700 psi 6,650 psi 3,520 psi 8,500 psi
ASTM C881 Bond Strength 7 days Neat Extended	3,790 psi 2,670 psi
AASHTO T97 Flexural Strength 7 days Neat Extended	3,440 psi 3,070 psi
AASHTO T198 Tensile Strength 7 days	2,330 psi

DIRECTIONS

Surface Preparation: Concrete must be free of coatings, dirt, oil, or other contaminants. Concrete must be frost free and dry. Sandblast all exposed reinforcing steel to remove all rust. Prepare forms when needed.

When priming the surface: It is preferable, but not required, to prime surfaces. When priming the surface with **Polytops MMA Kit**, use accelerator or retarder as needed (see Chart 1 on page 3) and add to **Part A Resin** then mix for one minute. Add **Part B Catalyst** (see Chart 1 page 3) and mix additional 2 minutes. Distribute the blended resin over the surface and brush in. To increase the working time and reduce the reaction speed it is critical to reduce the mass of blended resin by dispersing quickly over the surface.

Note: Do not add **Part C Aggregate** to prepared primer.



ChemMasters®

An American Owned & Operated Company
300 EDWARDS STREET • MADISON, OHIO 44057-3112 (440) 428-2105 • FAX (440) 428-7091 • ORDERLINE: (800) 486-7866 www.chemmasters.net

August 2018

When mixing a full unit:

- Use a heavy duty 1/2" or larger drill equipped with a jiffier type mixing prop or mortar mixer.
- Pour **Part A Resin** into a clean container with a minimum capacity of 6 gallons (22.7 L).
- Consult **Chart 1 Polytops MMA Grout Dosing & Mixing Chart** to determine the necessary amount of **Part B Catalyst** and **Accelerator** or **Retarder** based upon ambient air temperature.
- Add measured **Accelerator** or **Retarder** to **Part A Resin** and mix 1 minute.
- Add measured amount of **Part B Catalyst** and mix 1 minute.
- Avoid incorporating excess air into the mix. Add all of the premeasured **Part C Aggregate** slowly while continuing to mix the grout. Blend until all aggregate is coated and thoroughly wet out at least 2 to 3 minutes.

Application: Prepare a form for **Polytops MMA Grout** and pour the material into place.

Cleanup: When operations are completed or interrupted for more than 15 minutes, the mixing vessel and application tools must be cleaned. Clean tools and equipment before material dries and sets with xylene (xylol) or **Part A Resin** of the **Polytops MMA Grout kit**. If **Part A Resin** is used for cleaning, it can be saved and used for the next mix or saved for future cleaning. Adding coarse aggregate to the mixer while cleaning aids in removing the polymer grout.

STORAGE

Store factory sealed containers of unmixed material at 50 to 75°F (10 to 21°C) temperatures away from direct sunlight and sources of heat. Temperatures in excess of 75°F (21°C) cause premature aging of the material. Shelf life of properly stored material is two years from date of manufacture.

LIMITATIONS

- **Polytops MMA Grout** is exothermic, generating a large amount of heat when initially mixed. After mixing immediately pour all of the material to dissipate heat.
- When mixing a full unit, it is important to use all of **Part A Resin** and **Part C Aggregate** provided in each unit to obtain proper mix ratio and consistency
- **Polytops MMA Grout** is extremely fast setting. Substrate and forms must be ready as needed before material is mixed
- Good ventilation of the repair area is recommended to aid in the thorough cure of **Polytops MMA Grout**

PRECAUTIONS

Resin: Danger: Highly Flammable Liquid and Vapor. Harmful if swallowed. Harmful in contact with skin. Harmful if inhaled. Causes skin irritation. May cause an allergic skin reaction. Causes serious eye damage. May cause respiratory irritation. Harmful to aquatic life with long lasting effects.

Catalyst: Danger. Heating may cause a fire. May cause allergic skin reaction. Causes eye irritation. May cause respiratory irritation. Suspected of damaging fertility or the unborn child. Very toxic to aquatic life. May cause long lasting harmful effects to aquatic life.

Filler: WARNING. Suspected of causing cancer. May cause damage to lungs through prolonged or repeated exposure if inhaled.

KEEP OUT OF REACH OF CHILDREN

Proper application is the responsibility of the user. ChemMasters can only make technical recommendations and cannot provide quality control on the jobsite.

This Product is Formulated and Labeled for Industrial and Commercial Use Only

FOR BEST RESULTS AND SAFEST USAGE, USER IS SPECIFICALLY DIRECTED TO CONSULT THE CURRENT MATERIAL SAFETY DATA SHEET AND PACKAGE LABEL FOR THIS PRODUCT. We warrant our products to meet our published specifications and to be free from defects in materials and workmanship to the acceptable quality levels defined in these specifications. If acceptable quality levels are not specified, the acceptable quality levels will be those normally supplied by us for the product. We make no guarantee of the results to be obtained from the use of our products. The determination as to the adaptability of any of our products to the specific needs of the Buyer is solely Buyer's prerogative and responsibility. We are glad to offer suggestions on the use of our products. Nevertheless, there are no warranties given except such expresses warranties offered in connection with the sale of a particular product. Our liability shall be limited to replacement of, or refund of an amount not to exceed the purchase price attributed to, the goods as to which such claim is made. Our selection of one of these alternatives shall be Buyer's exclusive remedy. IN NO CASE SHALL WE BE LIABLE FOR CONSEQUENTIAL OR SPECIAL DAMAGES, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. THE FOREGOING WARRANTIES ARE IN LIEU OF ALL OTHER WARRANTIES, GUARANTEES, CO-CONDITIONS AND REPRESENTATIONS, EITHER EXPRESSED OR IMPLIED, WHETHER ARISING UNDER ANY STATUTE, COMMON LAW, USAGE OR TRADE, COURSE OF DEALING OR OTHERWISE, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE 2001ChemMasters made in the U.S.A.



Chart 1

Polytops MMA Grout Dosing & Mixing Chart

ALWAYS FOLLOW THE PROPER ORDER OF ADDITION					
Order of Addition	1	2	3	4	5
Ambient Air Temperature	Polytops MMA Grout Resin Part A	Polytops MMA Grout Accelerator	Polytops MMA Grout Retarder	Polytops MMA Grout Catalyst Part B	Polytops MMA Grout Aggregate Part C
100°F (37.8°C)	1.00 gal.	0.00 fluid oz.	1.50 fluid oz.	7 fluid oz.	70 lbs.
90°F (32.2°C)	1.00 gal.	0.00 fluid oz.	0.75 fluid oz.	7 fluid oz.	70 lbs.
80°F (26.7°C)	1.00 gal.	0.00 fluid oz.	0.25 fluid oz.	7 fluid oz.	70 lbs.
70°F (21.1°C)	1.00 gal.	0.00 fluid oz.	0.00 fluid oz.	7 fluid oz.	70 lbs.
60°F (15.6°C)	1.00 gal.	0.00 fluid oz.	0.00 fluid oz.	9 fluid oz.	70 lbs.
50°F (10°C)	1.00 gal.	0.00 fluid oz.	0.00 fluid oz.	12 fluid oz.	70 lbs.
40°F (4.4°C)	1.00 gal.	0.00 fluid oz.	0.00 fluid oz.	14 fluid oz.	70 lbs.
30°F (-1.1°C)	1.00 gal.	0.50 fluid oz.	0.00 fluid oz.	14 fluid oz.	70 lbs.
20°F (-6.7°C)	1.00 gal.	1.00 fluid oz.	0.00 fluid oz.	14 fluid oz.	70 lbs.
10°F (-12.2°C)	1.00 gal.	1.50 fluid oz.	0.00 fluid oz.	14 fluid oz.	70 lbs.
0°F (-17.8°C)	1.00 gal.	2.00 fluid oz.	0.00 fluid oz.	14 fluid oz.	70 lbs.

Never mix the MMA Accelerator or MMA Retarder directly with the Part C Catalyst.

Always add the Polytops MMA Accelerator to the Polytops MMA Grout Resin and mix before adding Part B Catalyst.

The Part B Catalyst must be dissolved in the Part A Resin before adding Part C Aggregate.

ChemMasters, Inc. * 300 Edwards Street * Madison, OH 44057 * Phone: 800-486-7866 * www.chemmasters.net